

**TECHNICAL PRODUCT DATA**

**TSR 20 RUBBER**

- Chemical characterization: natural rubber (NR) consisting essentially of cis-1,4-Polyisoprene with small amounts of non-rubber constituents (Proteins, Lipids).
- TSR 20 is produced from field grade material (coagulum).
- Change in physical state 10 - 35 °C after long periods of storage.
- Combustion with restricted access of air can result in the evolution of carbon monoxide gas.
- Packing in wooden palletcrates or shrinkwrapped on pallet bases.
- TSR 20 has proved to have good technological properties, and has become a large volume grade.

	<b>Specifications</b>	<b>Test method</b>
<b>Dirt</b>	Max. 0.20 %	ISO 249
<b>Ash</b>	Max. 1.00 %	ISO 247
<b>Volatile Matter</b>	Max. 0.80 %	ISO 248
<b>N2</b>	Max. 0.60 %	ISO 1656
<b>P<sub>0</sub></b>	Min. 30	ISO 2007
<b>P.R.I.</b>	Min. 40	ISO 2930

Date:18/03/2010

