

TECHNICAL PRODUCT DATA

TSR CV 60 RUBBER

- Chemical characterization: natural rubber (NR) consisting essentially of cis-1,4-Polyisoprene with small amounts of non-rubber constituents (Proteins, Lipids).
- TSR CV 60 is produced from high quality wholefield latex, bulked and acid coagulated under controlled conditions.
- TSR CV 60 rubber has a low ash and dirt content.
- Change in physical state 10 - 35 °C after long periods of storage.
- Combustion with restricted access of air can result in the evolution of carbon monoxide gas.

	Specifications	Test method
Dirt	Max. 0.05 %	ISO 249
Ash	Max. 0.60 %	ISO 247
Volatile Matter	Max. 0.80 %	ISO 248
N2	Max. 0.60 %	ISO 1656
P₀	--	
P.R.I.	Min. 60	ISO 2930
Mooney Viscosity ML (1'+4')100°C.	60 ±5	ISO 289

Date:18/03/2010

